

201

BITUMINOUS PRIMER

SEALER OR PRIMER FOR ALL POROUS AND NON-POROUS SURFACES

PRODUCT DESCRIPTION:

Serves as a primer for all bituminous systems, including Pro-Struct 1001 Plain, Pro-Struct 1001M, Pro-Struct 1002 and Pro-Struct 1003.

SPECIFICATION:

Surfaces to be coated with Pro-Struct 201 Bituminous Primer at a rate of \pm 3 to 5m²/litre, depending on surface porosity. On very porous surfaces, a second coat may be necessary.

MIXING:

Stir well before use, using a flat paddle.

INSTRUCTIONS:

Surfaces must be clean, sound and dry. All surfaces must be free from oils and grease and laitance removed from cementitious surfaces. Pro-Struct 201 is a one-part bituminous primer and is ready for use. Application must be done by brush or roller. Primer must be allowed to dry completely prior to overcoating to prevent entrapment of solvents.

CLEANING:

Brushes are to be cleaned by using Pro-Struct 105 Epoxy Brush Cleaner and washed off with soap and water. Clean hands with a solvent-wetted rag.

TYPICAL PROPERTIES AT 25°C

Colour Black

Shelf Life 24 Months

Number of Components 1

Coverage ± 3 to 5m²/litre/coat

Apply Over Clean, dry surfaces

Flash Point 30°C

Drying Times 2 to 4 Hours

Solids % Mass 32%

Application Temperature 10 to 35°C

Overcoat Time 4 to 6 Hours

Shelf Life 12 Months

VOC 569 g/l

Safety: Material is flammable and the necessary safety precautions need to be taken in the handling of this product.

May 2020 replaces October 2017

(Pro-Struct 201)